

#### **Commercial Solutions Division**

# 3M™ Controltac™ Graphic Film

162-10: IJ162-10

Product **Description** 

3M™ Controltac™ Graphic Film 162-10 / IJ162-10 is a polymeric calendered film that can be used, in combination with the designated protecting overlaminate, to produce outstanding resistant graphics for floors.

This film uses 3M™ Controltac™ technology.

3M™ Controltac™ minimizes the initial contact area of the adhesive and allows the applicator to reposition

the film during application.

This allows easier installation of large format graphics in a wide temperature range.

Product Line Screen printing white, opaque, semi-matte, removable adhesive (grey). 162-10

> Inkjet printing IJ162-10 white, opaque, semi-matte, removable adhesive (grey).

**Product Characteristics** 

These are indicative values for unprocessed products.

Contact your 3M representative for a custom specification.

Physical & Application

Material calendered vinyl (polymeric)

Surface finish semi-matte Thickness (film) 100 µm (0.1 mm)

Adhesive type solvent acrylic, pressure-sensitive, repositionable

Adhesive appearance grey, except for transparent versions double-sided Polyethylene coated paper Liner

Adhesion 7 N/25 mm FTM 1: 180° peel, substrate: glass; cond:

24 h 23°C/50%RH

Application method dry only!

< 1.0 mm FTM 14 Applied shrinkage +10°C

Application temperature for flat surfaces Service temperature 0°C to +65°C (not for extended periods of time at the extremes)

(after application)

Storage Shelf life

Surface type

Substrate type ceramic, finished wood, marble, sealed concrete, terrazzo, waxed vinyl Graphic removal Removable without heat and/or chemicals from supported substrates.

No liability is given for ease or speed of removal of any graphic. Pay attention to

adequate air and substrate temperature.

The values above are the results of illustrative lab test measurements and shall not be considered as a commitment from 3M.

Use within two years from the date of manufacture on the sealed original box. Use within one year after opening the box.

Storage conditions +4°C to +40°C, out of sunlight, original container in clean and dry area.

The shelf life as defined above remains an indicative and maximum data, subject to many external and noncontrollable factors. It may never be interpreted as warranty.

Flammability standards are different from country to country. Ask your local 3M contact for details, please. Flammability

#### **Durability**

The durabilities mentioned in the table below are the results of illustrative lab tests. The values show the best performance expected from these products, provided that the film will be processed and applied professionally according to 3M's recommendations.

The durability statements do not constitute warranties of quality, life and characteristics.

The durability of products is also influenced by:

- the type of substrate and thorough preparation of the surface (with 3M™ Surface Preparation System)
- application procedures
- environmental factors
- the method and the frequency of cleaning

Unprocessed film The following durability data are given for unprocessed film only!

Climatic zones Graphic durability is largely determined by the climate and the angle of exposure.

Find below a table showing the durability of a product according to the angle of

exposure and the geographical location of the application.

Zone 1 Northern Europe, Italy (north of Rome), Russia

Zone 2 Mediterranean area without North Africa, South Africa

Zone 3 Gulf area, Africa

**Exposure types** Vertical:

The face of the graphic is ±10° from vertical.

Interior means an application inside a building without direct Interior:

exposure to sunlight.

Interior application	Zone 1	Zone 2	Zone 3
interior	12 months	12 months	12 months

3M™ Performance Guarantee and MCS™ Warranty

In addition, 3M provides a guarantee/warranty on a finished applied graphic within the framework of 3M™ Performance Guarantee and/or 3M™ MCS™ warranty programs.

For detailed graphic construction and application options along with specific Warranty periods, please see the Warranty matrices and Warranty information on 3M Graphic Solutions/Warranties.

Visit www.3mgraphics.com for getting more details about 3M's comprehensive

graphic solutions.

# **End Uses**

Limitations of 3M specifically does not recommend or warrant the following uses, but please contact us to discuss your needs to recommend other products.

Graphics applied to

- exterior applications.
- purposes other than graphics for floors/pavements.
- substrates other than recommended.
- areas with vehicle traffic except for light slow moving traffic.
- loose, broken or unsound flooring material.

Graphics subjected to Important Notice

- gasoline vapors or spills.
- 3M Commercial Solutions products are not tested against automotive manufacturer specifications!
- Film has to be protected with the recommended protective overlaminate to provide the needed skid resistance.
- Place the floor graphic far enough away from entryways that they stay dry.

## Graphics Manufacturing

Graphic protection can improve the appearance, performance and durability of printed graphics. Any printed graphic exposed to abrasive conditions (including vehicles), harsh cleaners or chemicals must include graphic protection in order to be warranted.

When to use an overprint See instruction bulletin GPO 'graphic protection options' for further information about selection and use of clear or overlaminate protective overlaminates and printable clears.

Graphic for Floors To create a graphic for floors this film has to be protected with the recommended overlaminate. No printable clear available!

> Product Bulletin Graphic Protection Options <

Shipping finished graphics Flat, or rolled film side out on 130 mm (5 inch) or larger core. These methods help to prevent the liner from wrinkling or application tape, if used, from popping off.

### Converting Information

A too high total physical ink amount on the film results in media characteristic changes, inadequate drying, overlaminate lifting, and/or poor graphic performance. The maximum recommended total ink coverage for this film is 270%

Inkiet Printing Adequately Dry Graphics

Inadequate drying can result in graphic failure including curling, increased shrinkage and adhesion failure, which are not covered under any 3M warranty.

Poorly dried film becomes soft and stretchy, and the adhesive becomes too aggressive.

Even if your printer has a dryer, it may not adequate dry latex and solvent inks in the short period of time it spends passing through the heater.

Recommendations to improve the drying of solvent Dry the graphic unrolled or at least as a loose wound roll standing upright. To further increase air circulation place the spooled film roll on a grid, and place a fan beneath the grid.

If you only spool open the film, adequate drying could still take a week, depending on the environment.

Build enough time into your process to ensure adequate drying of the graphic. 3M recommends at least a minimum drying time of 24 hrs before further processing. Test: Fold a piece of film with maximum ink laydown of the graphic onto itself. Apply 140 g/cm² for 15 minutes, release and check for effects like sticking or dull spots. These are clear indications that further curing or drying is needed.

Notice: Latex inks are

Unlike solvent inks, spooling and letting latex printed graphics sit does not help to cure the ink, but does allow the graphic manufacturer to see if any oily spots are generated which may interfere with proper adhesion of overlaminates.

To ensure proper latex ink drying, use the following recommendations:

Media Presets: HP media presets contain all the needed settings to print on a specific media. Download and use media presets from the following page: www.hp.com/go/mediasolutionslocator. Environmental Conditions: HP media presets have been specially designed and tested for each printer-media combination. Recommended environmental conditions: +20°C to +25°C, Humidity 40% - 60% RH

831/871 and HP 881/891

Important notice for HP The amount of ink printed is the main key for proper overlaminate adhesion. Select a media preset using 100% or less ink density.

Post-processing of latex printed graphics immediately after printing

Latex inks should emerge from the printer fully dried. Post-air drying of a wet print will not enable drying, since latex ink drying requires that the dried ink is heated above the film formation temperature of the latex inside the printer.

For immediately post-processing of latex printed graphics follow strictly the recommendations given above (Section: Latex inks are different) and test the proper drying with the following performance tests:

Visual Test: Check the image immediately after printing. The sample should not be wet or sticky to the touch, or have an 'oily' feel when it emerges from the printer.

Rubbing Test: After the visual inspection, wipe the printed sample with a white wet paper towel. Fully-dried ink should resist wiping and should not show any stains on the white cloth. If the ink is easily removed by wet rubbing, then it is not dried.

Stacking Test: In some cases, the top surface will appear dry after printing but within a few minutes ink may migrate to the surface leaving an oily aspect. To ensure proper drying, stack at least 12 sheets liner to printed

After 1 hour, remove the stack and check for "oily" stains, wet surfaces or glossiness changes on high ink laydown areas on each sheet. If any of these occur, then the ink is not properly dried.

If a sample is not properly dried on the printer, reprint the image under a condition that allows complete drying. Common improvement steps are:

- Increasing the drying temperature in 5 degree steps.
- Increasing the number of passes to slow down printing.
- Reducing the amount of ink printed (media preset with lower ink densities).

Allow the converted graphic to build sufficient

Give laminated samples time before applying them. The adhesion bond between the laminate and the printed base film will increase with time. 24 hours minimum for room temperature laminated graphics.

bond prior to

8 hours minimum for graphics laminated with heated rolls (one or two). Lamination temperature: +40°C to application/installation +60°C. Lamination speed: maximum 2 meter/minute.

### Converting Information

Formulations and processing conditions can affect ink durability. Refer to the 3M Product and Instruction Bulletins for your ink for limitations and proper usage. Graphic protection can improve the appearance, performance and durability of your graphic.

Screen Printing

A clear coat also prevents chalking on unprinted films. Use equipment designed to handle high viscosity materials and make sure the coating is evenly applied to the specifications given in the clear's Instruction Bulletin.

Loss of Gloss

Abrasion and Abrasion damage and loss of gloss are not covered by any 3M warranty. This is considered normal wear and

#### **Application**

See product bulletin ATR 'application tape recommendations' for information about selection and use of suitable application tapes for this product, please.

> Product Bulletin Application Tape Recommendations <

Refer to Instruction Bulletin 5.1 'select and prepare substrates for graphic application', for general application information.

>Instruction Bulletin 5.1 'select and prepare substrates for graphic application'<

Controltac™ Films

Important Notice Films require high squeegee pressure to avoid air entrapment between film and substrate. Therefore the use of 3M™ PA-1 Gold Squeegee with thin and soft sleeve is recommended. Wetting of sleeves helps to avoid scratches on film surface during application. Please refer to the product's instruction bulletin for detailed information.

Graphics for Floors Application Tapes

Graphic for floors do not require a premask or prespacing tape for application.

**Avoid Lifting** 

Cut radiuses on any sharp corners of the graphic after lamination. Do not apply finished graphic to the edge of tiles. Keep always a distance of a few centimeter to the joints (not edge of graphic to edge of tile).

## Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline).

Refer to Instruction Bulletin 6.5 'storage, handling, maintenance and removal of films and sheetings', for general maintenance and cleaning information.

>Instruction Bulletin 6.5 'Storage, Handling, Maintenance and Removal of Films and Sheetings'<

#### Remarks

This bulletin provides technical information only.

Important notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.

Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.

As outdoor graphics age, natural weathering occurs causing a gradual reduction in gloss, slight color changes, some lifting of the graphic at the edges or around rivets, and ultimately a minor amount of cracking.

These changes are not evidence of product failure and are not covered by a 3M warranty.

Additional information Visit the web site of your local subsidiary at www.3Mgraphics.com for getting:

- more details about 3M™ MCS™ Warranty and 3M™ Performance Guarantee
- additional instruction bulletins
- a complete product overview about materials 3M is offering



Responsible for this technical bulletin

Commercial Solutions Division Hermeslaan 7 1831 Diegem, Belgium

3M Deutschland GmbH Carl-Schurz-Str. 1 41453 Neuss, Germany

3M. Controltac, Envision, Scotchcal, Comply, MCS, and Panagraphics are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.